ORIGIN AND MITIGATION OF THE BEAM-INDUCED SURFACE MODIFICATIONS OF THE LHC BEAM SCREENS

V. Petit^{*}, P. Chiggiato, M. Himmerlich, S. Marinoni, H. Neupert, M. Taborelli, L. Tavian European Organization for Nuclear Research, CERN, Geneva, Switzerland

Abstract

maintain attribution to the author(s), title of the work, publisher, and DOI

must 1

work

of this

Any distribution

4.0 licence (© 2022).

CC BY

the

of

terms

the

under a

used

ē

mav

work

from this

Content

. ()

All over Run 2, the LHC beam-induced heat load on the cryogenic system exhibited a wide scattering along the ring. Studies ascribed the heat source to electron cloud build-up, indicating an unexpected high Secondary Electron Yield (SEY) of the beam screen surface in some LHC regions. The inner copper surface of high and low heat load beam screens, extracted during the Long Shutdown 2, was analysed. On the low heat load ones, the surface was covered with the native Cu₂O oxide, while on the high heat load ones CuO dominated at surface, and it exhibited a very low carbon coverage. Such chemical modifications increase the SEY and inhibit a proper conditioning of the affected surfaces. Following this characterisation, the mechanisms for CuO build-up in the LHC beam pipe were investigated on a newly commissioned cryogenic system allowing electron irradiation, surface chemical characterisation by X-ray Photoelectron Spectroscopy and SEY measurements on samples held below 15 K. In parallel, curative solutions against the presence of CuO in the LHC beam screens were explored, which could be implemented in-situ to recover a proper conditioning and lower the beam-induced heat load.

INTRODUCTION

An unexpected high beam-induced heat load was measured in the beam screen cooling circuit of half of the eight LHC arcs all over Run 2 (2015-2018). This puzzling data was detected first after the Long Shutdown 1 (LS1), a period of maintenance and upgrade including the venting of the cryogenic beam vacuum system to air [1]. Surface analyses were performed on the copper layer of beam screens extracted from the accelerator during the LS2 (2019-2021). The measurements evidenced the presence of native Cu₂O oxide on the surface of the low heat load beam screens, while the high heat load ones were oxidized to non-native CuO oxide and showed an exceptionally low carbon coverage [2]. In addition, the Secondary Electron Yield (SEY) of the beam screens after extraction was found higher when CuO was present. Finally, the room temperature conditioning by electron irradiation of CuO-rich surfaces was observed to be moderate compared to the one of Cu₂O, but not completely inhibited, and CuO was observed to be partially reduced to Cu₂O [2]. This reduction could be hindered or slowed down in the operating conditions of the beam screens, namely between 5 and 20 K, leading to the survival of a high-SEY oxide in some LHC beam screens, to an intense electron cloud activity and to the related high beam-induced heat load. Here, the behaviour of CuO under

*valentine.petit@cern.ch

electron irradiation in cryogenic conditions and the origin of its build-up in some LHC beam screens are assessed. In addition, possible techniques for in-situ CuO reduction are reviewed.

CONSEQUENCE AND ORIGIN OF CuO BUILD-UP IN THE LHC

The cryo-conditioning tests performed in this work were carried out on a new system enabling X-ray photoelectron spectroscopy (XPS), electron irradiation and SEY measurement (part still under commissioning) of samples below 15 K. Irradiation was performed by 250 eV electrons.

Cryo-conditioning of CuO

The fraction of CuO at the surface of beam screen samples was deduced from XPS measurements of the Cu $2p_{3/2}$ state [3]. CuO fraction evolution during electron irradiation at 250 eV, both at room temperature and 15 K, is shown in Fig. 1.



Figure 1: Effect of temperature on CuO reduction under electron irradiation at 250 eV (lines are guide to the eye).

CuO reduction is significantly hindered at 15 K, possibly because of the reduced diffusivity of Cu and O ions in the oxide layer at cryogenic temperature. Therefore, the build-up and the stability of this high-SEY oxide at cryogenic temperature together with the low content of carbon, which limits the graphitic coverage essential for SEY decrease [4, 5], could be responsible for the high beam-induced heat load occurring in some regions of the LHC arcs.

Origin of CuO build-up

Copper hydroxide Cu(OH)₂, which spontaneously grows on air-exposed copper surfaces [6], has been proposed as a precursor for CuO build-up in the LHC [2]. However, room temperature conditioning of airborne Cu(OH)₂ layers led to their conversion to Cu₂O, i.e. a reduction to Cu⁺, which has a sufficiently low SEY [5]. Nevertheless, also in this case, temperature is expected to play a major role in elec-

13th Int. Particle Acc. Conf.	IPAC2022, Bangkok, T	Thailand	JACoW Publishing
ISBN: 978-3-95450-227-1	ISSN: 2673-5490	doi:10.184	29/JACoW-IPAC2022-TUOXSP1

tron irradiation-induced reactions by affecting diffusion kinetics. Another factor which influences the species formed or decomposed by electron irradiation is the presence of carbon on oxidized Cu surfaces. The absolute carbon coverage is known to influence the chemical transformation during electron bombardment [7] and could thus be decisive to determine the build-up or not of CuO.

The observed modifications of air-exposed copper samples during conditioning at room and cryogenic temperatures are reported in Fig. 2, and the ones for conditioning at 15 K of samples with different carbon coverages are shown in Fig. 3. In these figures, the evolution of the chemical state of copper during conditioning, as monitored by XPS, is followed for different doses through a Wagner-like plot [2, 3], where the usual Cu $2p_{3/2}$ binding energy axis is replaced by the centre of gravity of this line, to account for the presence of multiple compounds [2]. The position of reference CuO, Cu(OH)₂, Cu₂O and Cu(0) samples is shown for comparison.



Figure 2: Conditioning of twin air-exposed copper samples at room temperature and 15 K.



Figure 3: Conditioning at 15 K of air-exposed copper samples with different initial carbon coverages.

Figure 2 clearly shows the influence of temperature on the type of oxide dominating the surface after conditioning. While the conditioning at room temperature provokes the transformation of Cu(OH)₂ into Cu₂O, the conditioning at 15 K of a twin sample deviates towards CuO. The formed CuO-like product is similar to the one observed in the

the final

LHC-extracted beam screens, where the oxide observed after extraction was even closer to reference CuO in extreme cases [2].

Figure 3 shows the conditioning behaviour at 15 K of two copper samples with initially identical amount of copper hydroxide, but different carbon coverages (23 and 50 at.%). In the presence of high carbon coverage, conditioning leads to significant, but still incomplete, reduction of $Cu(OH)_2$ to Cu_2O , i.e. the dehydration of $Cu(OH)_2$ to CuO is partially avoided. In addition, the carbon content drops to 35 at.%, as expected for a consumption of carbon species during the oxide reduction [7]. At low carbon coverage, Cu(OH)2 is converted to CuO and the amount of carbon drops to 7.5 at.%, which is extremely low and is compatible with the amount of carbon found on the CuO-rich LHC-extracted beam screens [2].

To reproduce the Run 1 - LS1 - Run 2 LHC scheme and propose a scenario leading to CuO build-up only after LS1 in the accelerator, a copper sample exposed to air for more than a year and showing 40 at.% of carbon has been first conditioned at 15 K and then reconditioned at 15 K after 2.5 months of humid air exposure. The corresponding Wagner-like plot is given in Fig. 4.



Figure 4: Conditioning and reconditioning at 15 K of an air-exposed copper sample.

Thanks to the initial carbon coverage, the transformation of Cu(OH)₂ into CuO is partially inhibited during the first conditioning. In parallel, the carbon content decreases and stabilizes to 31 at.% at the end of this conditioning. After 2.5 months of humid air exposure, Cu(OH)₂ coverage is significantly higher than for a non-conditioned sample stored in the same conditions. Indeed, in the current case, the formed layer is even similar to the one of a reference Cu(OH)₂ sample, pointing towards an increased surface reactivity after conditioning due to electron irradiation. Subsequently, the second conditioning leads to the transformation of Cu(OH)₂ to CuO. This difference of oxidation product formed under electron irradiation could be due to the higher amount of Cu(OH)₂ before the second irradiation, but also, as discussed before, to the lower amount of carbon, already partially depleted during the first conditioning. The carbon decrease had stabilized at the end of the first conditioning, but continued to decrease down to 13 at.% during the second irradiation, again compatible 13th Int. Particle Acc. Conf. ISBN: 978-3-95450-227-1

and DOI

publisher.

title of the work,

attribution to the author(s).

2022). Any distribution of this work must maintain

0

4.0 licence

the CC BY

terms of

the

under

used

ę

may

work

with carbon consumption by reaction with oxygen from the oxide or hydroxide [7]. In summary, this conditioning – air exposure – reconditioning sequence and the resulting surface modifications are compatible with the observed heat load increase in some arcs comparing LHC Runs 1 and 2.

MITIGATION TECHNIQUES

In parallel to the investigations on the origin of CuO build-up in the LHC, in-situ curing methods have been explored. All of them are based on the removal of CuO from the surface by a reaction with a reducing gas promoted by various sources of energy. For this purpose, samples have been exposed to UV light and to atmospheric pressure plasma, both in 1 bar of N₂-H₂ (95%-5%) mixture. Other samples were exposed to atomic hydrogen generated on a hot tungsten filament (H₂ pressure: 10^{-2} mbar). The Cu $2p_{3/2}$ spectra of a CuO reference sample before treatment, as well as the ones of three samples treated by the different techniques are shown in Fig. 5.



Figure 5: Cu $2p_{3/2}$ spectra of CuO sample before and after various treatments.

In all cases, a complete CuO reduction is obtained, as witnessed by the complete disappearance of the CuO satellite between 939 eV and 945 eV. These techniques seem therefore promising for an in-situ deoxidation of the LHC beam screens.

CONCLUSION

Thanks to a newly commissioned cryogenic system equipped for XPS analysis and electron irradiation, it is demonstrated that CuO is not reduced during conditioning by electron irradiation at 15 K. The build-up and the stability of this high-SEY oxide together with a low carbon coverage in some part of the LHC arcs can thus be responsible for high beam-induced heat load via intense electron cloud activity. In parallel, conditioning tests at 15 K of Cu(OH)₂covered copper surfaces with various amounts of carbon allowed to propose a scenario explaining the observed oxidation state and the associated high heat load of some LHC beam screens. The following sequence is proposed: at the start of LHC Run 1, the beam screens exhibited either a low Cu(OH)₂ coverage and/or a large carbon content, which led to a normal (CuO-free) conditioning during Run 1, with possible start of carbon depletion \rightarrow the high surface reactivity after electron irradiation during Run 1 enhanced hydroxide formation due to air-exposure during LS1, possibly influenced by the local ambient conditions \rightarrow a local high Cu(OH)₂ and low carbon coverage then led to CuO build-up during Run 2. CuO-free beam screens could have resulted from conditioning of surfaces with low Cu(OH)₂ coverage or high carbon content at the end of LS1.

Techniques for in-situ deoxidation of the beam screens have been explored on a laboratory test bench and reduction of CuO is possible by exposure to reducing gas activated either by UV light or in an atmospheric pressure plasma, as well as by exposure to atomic hydrogen formed on a hot tungsten filament. The compatibility of these techniques with an in-situ implementation is under investigation and a further step is required to assess and avoid possible recurrence of CuO on the treated surfaces.

ACKNOWLEDGEMENTS

The authors would like to thank the CERN Beam-Induced Heat Loads Task Force for the support along this study.

REFERENCES

- G. Iadarola *et al.*, "Progress in Mastering Electron Clouds at the Large Hadron Collider," in *Proc. 12th Int. Particle Accelerator Conf. (IPAC'21)*, Online, May 2021. pp. 1273-1278. doi:10.18429/JACOW-IPAC2021-TUXA03
- [2] V. Petit *et al.*, "Beam-induced surface modifications as a critical source of heat loads in the Large Hadron Collider," *Commun. Phys.*, vol. 4, no. 1, pp. 1–10, 2021.
 doi: 10.1038/s42005-021-00698-x
- [3] M. C. Biesinger, "Advanced analysis of copper X-ray photoelectron spectra," *Surf. Interface Anal.*, vol. 49, no. 13, pp. 1325–1334, 2017. doi: 10.1002/sia.6239
- [4] R. Cimino *et al.*, "Nature of the decrease of the secondaryelectron yield by electron bombardment and its energy dependence," *Phys. Rev. Lett.*, vol. 109, no. 6, p. 064801, 2012. doi: 10.1103/PhysRevLett.109.064801
- [5] V. Petit, M. Taborelli, H. Neupert, P. Chiggiato, and M. Belhaj, "Role of the different chemical components in the conditioning process of air exposed copper surfaces," *Phys. Rev. Accel. Beams*, vol. 22, no. 8, p. 083101, 2019. doi: 10.1103/PhysRevAccelBeams.22.083101
- [6] T. L. Barr, "An ESCA study of the termination of the passivation of elemental metals," J. Phys. Chem., vol. 82, no. 16, pp. 1801–1810, 1978. doi: 10.1021/j100505a006
- [7] A. Losev, K. Kostov, and G. Tyuliev, "Electron beam induced reduction of CuO in the presence of a surface carbonaceous layer: an XPS/HREELS study," *Surf. Sci.*, vol. 213, pp. 564–579, 1989.

doi:10.1016/0039-6028(89)90313-0